

## Description

**Polypropylene 4720WZ** is a nucleated impact copolymer with a Melt Flow of 25 g/10min.

4720WZ is characterized by improved stiffness, creep resistance, high impact resistance, excellent antistatic properties and has been formulated to allow faster cycling through early demolding.

4720WZ has been developed specifically for the injection molding of garden furniture, housewares and thin-walled articles.

## Characteristics

	Method	Unit	Typical Value
<b>Rheological Properties</b>			
Melt Flow	ASTM D-1238	g/10 min	25
<b>Mechanical Properties</b>			
Tensile, Strength at Yield	D-638	psi (MPa)	4,000 (28)
Elongation at Yield	D-638	%	6
Flexural Modulus	D-790	psi (MPa)	210,000 (1,450)
Izod Impact Notched @ 23°C @ -20°C	D-256	ft.-lbs/in. (J/m)	2.0 (107)
	D-256	ft.-lbs/in. (J/m)	0.9 (48)
Charpy Impact Strength @ 23°C @ -20°C	DIN 53453	kJ/m <sup>2</sup>	9.5
	DIN 53453	kJ/m <sup>2</sup>	4.5
<b>Thermal Properties<sup>(1)</sup></b>			
Melting Range	TOTAL Method	°F (°C)	320-329 (160-165)
Heat Deflection	D-648	°F (°C)	194 (90)
Vicat Softening Point	D-1525	°F (°C)	302 (150)
<b>Other Physical Properties</b>			
Density	D-1505	g/cm <sup>3</sup>	0.905

(1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.

4720WZ 01/2020



TOTAL PETROCHEMICALS & REFINING USA, INC.  
 POLYMERS AMERICAS  
[www.totalrefiningchemicals.com](http://www.totalrefiningchemicals.com)  
 1201 Louisiana Street  
 Suite 1800  
 Houston, TX 77002

TECHNICAL CENTER  
 P.O. Box 1200  
 Deer Park, Texas 77536  
 Phone: 281-884-7500

**1-800-344-3462**