

Description

Polystyrene 825E: Designed specifically for extrusion/thermoforming. The polymer's balanced properties and processing characteristics make it especially suitable for industrial packaging deep draw thermoforming and custom multilayer sheet extrusion. Over the years, this popular resin has established itself as the industry standard extrusion grade high impact polystyrene.

Application:

- Custom sheet extrusion
- Extrusion thermoforming
- Packaging applications
- Form – Fill – Seal applications

General Information:

- This material complies with FDA requirements as described in 21 CFR §177.1640.
- This material holds Underwriters Laboratory recognition 94HB; see UL File E55470 at www.UL.com.
- USP Class VI
- Material Safety Data Sheets are available to help customers satisfy their safety needs.

Characteristics

| | Method | Unit | Typical Value |
|----------------------------------|--------|------------------------|---------------|
| Rheological Properties | | | |
| Melt Flow (200°C-5kg) | D-1238 | g/10mn | 3.0 |
| Mechanical Properties | | | |
| Falling Dart | D-3029 | in-lb | 110 |
| Izod - notched | D-256 | ft-lbs/in | 2.3 |
| Tensile Strength | D-638 | psi | 3,600 |
| Tensile Modulus | D-638 | psi (10 ⁵) | 3.0 |
| Elongation | D-638 | % | 50 |
| Flexural Strength | D-790 | psi | 6,900 |
| Flexural Modulus | D-790 | psi (10 ⁵) | 3.2 |
| Thermal Properties | | | |
| Heat Distortion - Annealed | D-648 | °F | 202 |
| Vicat Softening | D-1525 | °F | 215 |
| Other Physical Properties | | | |
| Gloss | D-523 | 60° | 70 |
| Density | | g/cm ³ | 1.04 |
| Linear Shrinkage | D-955 | in/in | .004 - .007 |
| Moisture | | % | <0.1 |

825E 01/2020

Polystyrene


 TOTAL PETROCHEMICALS & REFINING USA, INC.
 POLYMERS AMERICAS
www.totalrefiningchemicals.com
 1201 Louisiana Street
 Suite 1800
 Houston, TX 77002

 TECHNICAL CENTER
 P.O. Box 1200
 Deer Park, Texas 77536
 Phone: 281-884-7500

1-800-344-3462